

**Vertex** Dental

# Heat-Curing acrylics



### Heat-Curing acrylics indications:

- Denture base acrylics
- High Impact acrylic
- Relining acrylic

### Vertex™ Rapid Simplified



Vertex™ Rapid Simplified is a heat-curing denture base material and forms a solid base for full and partial dentures. The pressing technique is the processing method for Rapid Simplified. This cadmium-free acrylic has a rapid 20 minutes polymerisation cycle (also overnight polymerisation is possible). Flask to be put in boiling water.

### Vertex™ Regular & Regular Crystal Clear



Vertex™ Regular is a conventional heat-curing denture base material and forms a solid base of full and partial dentures. The pressing technique is the processing method for Vertex™ Regular. This cadmium-free acrylic has a conventional long polymerisation cycle. Flask to be put in cold water. Increase temp to 100° then a 30 min polymerisation cycle. Vertex™ Regular is the ideal hot-curing acrylic in tropical climates. Also available in Regular Crystal Clear.

### Vertex™ Implacryl



Vertex™ Implacryl is a heat-curing extra strong denture base material developed for the production of full and partial dentures and in particular for over-dentures on implants. The pressing technique is the processing method for Vertex™ Implacryl. Using high impact acrylic in implant work prevents breaking of dentures which can occur due to the lack of space. 2hrs polymerisation, 1½ hours at 70°C - 30 minutes at 100°C.

### Vertex™ Soft



Vertex™ Soft is a flexible denture soft lining acrylic (heat curing). Vertex™ Soft has an excellent adhesion to both new and existing dentures. The outstanding surface density makes the material simple to finish and polish with the special polishing instruments. Vertex™ Soft is for temporary use. Patients with continuous pain problems because they are wearing a denture are mostly helped with a Vertex™ Soft liner. To be applied on a heat cure basis. 2hrs polymerisation, 1½ hours at 70°C - 30 minutes at 100°C.

The following products are closely related to the Heat-Curing acrylics:



**Vertex™ Metal flasks**  
Upper, Lower and Clasp.



**Vertex™ Divosep**  
Separating plaster from denture base material and separating plaster from plaster.



**Vertex™ Divosheet**  
Is a highly flexible polyethylene sheet to be used in the trial pressing method & Vertex™ Soft.



**Vertex™ Shade guide**  
Denture base shade guide for hot & cold polymerising acrylics.

### Vertex-Dental B.V.

Johan van Oldenbarneveltlaan 62 | 3705 HJ Zeist  
P.O. box 10 | 3700 AA Zeist | The Netherlands  
Tel. +31 (0)30-69 76 749 | Fax +31 (0)30-69 55 188  
info@vertex-dental.com | www.vertex-dental.com